



Kobefab International
De Vest 62
555XP Valkenswaard
Nederland

Your notice of
 20-09-2019

Your reference

Date
 25-10-2019

Analysis Report 19.05287.02

Modification of analysis report 19.05287.01, made on 30-09-2019

Required tests :

IMO - 2010 FTP Code Annex 1 -
Fire test procedures - Part 8
IMO - 2010 FTP Code Annex 1 -
Fire test procedures - Part 8

Fire tests - Test for upholstered furniture - smouldering
cigarette test
Fire tests - Test for upholstered furniture - Match flame
equivalent

Identification number	Information given by the client	Date of receipt
T1920095	BERYL FR	20-09-2019



Petra Wittevrongel
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T1920095 - BERYL FR

IMO upholstered furniture

Information given by the client

Type of furniture Upholstery

Fabric

Composition Polyester

Structure Plain

Number of threads - warp 14/cm

Number of threads - weft 10/cm

Yarn count - warp 1500D

Yarn count - weft 1800D

Thickness in mm 1.8

Weight g/m² 568

Colour Beige

Treated with an FR finish/coating yes



Reference: T1920095 - BERYL FR

Fire tests - Test for upholstered furniture - smouldering cigarette test

Date of ending the test 27-09-2019
Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
Deviation from the standard -
Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling SB 36140 (Recticel) - fire retardant foam - $\pm 36 \text{ kg/m}^3$

Ignition source: smouldering cigarette with the following specifications

Length: $(70 \pm 4) \text{ mm}$

Diameter: $(8.0 \pm 0.5) \text{ mm}$

Mass: $(0.95 \pm 0.15) \text{ g}$

Smouldering rate: $(11.0 \pm 4.0) \text{ min} / 50 \text{ mm}$

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurrence of flames	no	no
	non-ignition	non-ignition

Conclusion Pass



Reference: T1920095 - BERYL FR

Fire tests - Test for upholstered furniture - Match flame equivalent

Date of ending the test 27-09-2019
Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling SB 36140 (Recticel) - fire retardant foam - $\pm 36 \text{ kg/m}^3$

Flame application time (s) 20

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 120 s	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	0	10
	non-ignition	non-ignition

Conclusion Pass