



Confidential Report

Our Ref: 56166-2-2



1066

Notified Body
for PPE Directive,
Construction Products Regulation
& Marine Equipment Directive
I.D. No. 0338 & 0339



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 16 April 2019

Our Ref: 56166-2-2
Your Ref: 2043

Page: 1 of 5

Client: Kobefab International B.V.
De Vest 62
5555 XP Valkenswaard
Netherlands

Job Title: Fire Test on One Sample of Fabric

Client's Order No: 2043

Date of Receipt: 15 March 2019

Description of Sample(s): One sample of fabric, referenced;
Craft CS 300cm, stated to be 100% Trevira CS

Work Requested: We were asked to make the following test(s):

IMO FTP Code 2010 Part 7

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.
Copyright © 2019 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

Website: www.bttg.co.uk

Date: 16 April 2019

Our Ref: 56166-2-2

Your Ref: 2043

Page: 2 of 5

Client: Kobefab International B.V.

Product Description

Company Name	Kobefab International bv
Type of Material, i.e. Curtain, Drape, etc.	Curtain, Drape, etc.
Name and/or Identification of the Product Tested	Craft CS
Mass per Unit Area (g/m ²)	Approx. 54 gr/sqmtr2
Thickness (mm)	1-2 mm
Colour and Tone (i)	Not supplied by client
Quantity and Number of Any Coating	Not supplied by client
Method and Quantity of Fire Retardant Treatment	100% inherent Trevira CS yarns
Materials of the Product and its Composite Ratio (ii)	100% Trevira CS yarns
Composition of Weave (iii)	Dobby weave
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Not supplied by client
Yarn Number Count	Not supplied by client

(i) If the product has a pattern, the representative colour shall be described.

(ii) Such as wool, nylon, polyester, etc.

(iii) Such as plain, weave, twilled;



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.

A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Limited

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2019 Shirley Technologies Limited. All rights reserved.

Date: 16 April 2019

Our Ref: 56166-2-2

Your Ref: 2043

Page: 3 of 5

Client: Kobefab International B.V.

FIRE TESTS ACCORDING to IMO FTP Code 2010:Part 7

Test for Vertically Supported Textiles and Films

Cleaning Procedure

The sample received no pre-treatment as the fabric was stated to be inherently flame retardant.

Conditioning

The sample was conditioned for 72 hours in the standard atmosphere for conditioning textiles of $20 \pm 5^\circ\text{C}$ and $65 \pm 5\%$ R.H.

Procedure

The sample was tested in accordance with IMO FTP Code 2010:Part 7. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

A 40mm high propane gas flame was applied to the edge of 5 warp and 5 weft specimens for 15 seconds.

The after-flame time, length of char, existence of surface flashing and ignition of cotton waste from drops were recorded.

Requirements

The Performance Criteria for Curtains and Drapes states that: Products which show any of the following characteristics obtained by the fire test in appendix 1, shall be considered unsuitable for use as curtains, drapes or free-hanging fabric product for use in rooms containing furniture and furnishings of restricted fire risk as defined in the relevant regulations of chapter II-2 of the Convention:-.

1. An after-flame time greater than 5 sec for any of the 10 or more specimens tested with surface application of the pilot flame.
2. Burn through to any edge of any of the 10 or more specimens tested with surface application of the pilot flame.
3. Ignition of cotton wool below specimen in any of the 10 or more specimens tested.
4. An average char length in excess of 150mm observed in any of the 10 or more specimens tested by either surface or edge ignition; and
5. The occurrence of a surface flash propagating more than 100mm from the point of ignition with or without charring of the base fabric.

If it is found that either or both of the batches of five specimens cut in both warp and weft directions fail to meet one or more of the criteria specified in subparagraphs .1 to .3 and .5 above because of poor performance of only one of the five specimens tested, one complete retest of a similar batch is permitted. Failure of the second batch to meet any of the criteria shall provide the basis for rejection of the fabric for use.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

Website: www.bttg.co.uk

Date: 16 April 2019

Our Ref: 56166-2-2

Your Ref: 2043

Page: 4 of 5

Client: Kobefab International B.V.

As Received


	After flame time (s)		Char length (mm)		Flaming to edge (yes or No)		Ignition of Cotton Wool from Flaming Drops (Yes or No)		Surface Flashing (Yes or No), if yes, Propagation Length (mm)	
	Warp	Weft	Warp	Weft	Warp	Weft	Warp	Weft	Warp	Weft
	0	0	42	54	No	No	No	No	No	No
	0	0	47	61	No	No	No	No	No	No
	0	0	62	39	No	No	No	No	No	No
	0	0	49	40	No	No	No	No	No	No
	0	0	52	47	No	No	No	No	No	No
Mean	0	0	50.4	48.2						


Comment

The results indicate the sample meets the requirements according to IMO 2010 FTP Code, Part 7.

This report relates only to the samples submitted and as described in the report.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Reported by: 
B Bland
Laboratory Technician

Countersigned By: 
P Doherty
Manager



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.
Copyright © 2019 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Client: Kobefab International B.V.

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

Website: www.bttg.co.uk

Date: 16 April 2019

Our Ref: 56166-2-2

Your Ref: 2043

Page: 5 of 5

Uncertainty Budget - Annex

The overall uncertainty budget IMO FTP Code 2010:Part 7 is as follows:-

Measurements: $\pm 1\text{mm}$
Duration of Flaming: ± 0.5 seconds



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.
Copyright © 2019 Shirley Technologies Limited. All rights reserved.