



# Confidential Report

**Our Ref: 23/57262-1-2**



1066

Notified Body  
for PPE Directive,  
Construction Products Regulation  
& Marine Equipment Directive  
I.D. No. 0338 & 0339



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 27 February 2020

Our Ref: 23/57262-1-2  
Your Ref: 2101

Page: 1 of 5

Client: Kobefab International B.V.  
De Vest 62  
5555 XP Valkenswaard  
Netherlands

Job Title: Fire Test on One Sample of Fabric

Client's Order No: 2101

Date of Receipt: 12 February 2020

Description of Sample(s): One sample of fabric, referenced;  
Olite FR 300cm, stated to be 100% Pes FR

Work Requested: We were asked to make the following test(s):

IMO FTP Code 2010 Part 7

- \* subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.  
BTTG™ and Shirley® are trade names of Shirley Technologies Limited  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.  
Our laboratories are accredited to EN ISO/IEC 17025.  
Copyright © 2020 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

**Client: Kobefab International B.V.**

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)

Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 27 February 2020

Our Ref: 23/57262-1-2

Your Ref: 2101

Page: 2 of 5

### Product Description

|                                                                                 |                            |
|---------------------------------------------------------------------------------|----------------------------|
| Company Name                                                                    | Kobefab International bv   |
| Type of Material, i.e. Curtain, Drape, etc.                                     | Curtain, Drape, etc.       |
| Name and/or Identification of the Product Tested                                | Olite FR 300cm             |
| Mass per Unit Area (g/m <sup>2</sup> )                                          | Approx. 35 gr/sqmtr2       |
| Thickness (mm)                                                                  | 1-2 mm                     |
| Colour and Tone (i)                                                             | Not supplied               |
| Quantity and Number of Any Coating                                              | Not supplied               |
| Method and Quantity of Fire Retardant Treatment                                 | 100% Inherent Pes FR yarns |
| Materials of the Product and its Composite Ratio (ii)                           | 100% Inherent Pes FR yarns |
| Composition of Weave (iii)                                                      | 100% Pes FR Leno Weave     |
| Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and | Not supplied               |
| Yarn Number Count                                                               | Not supplied               |

- (i) If the product has a pattern, the representative colour shall be described.
- (ii) Such as wool, nylon, polyester, etc.
- (iii) Such as plain, weave, twilled;



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Limited

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)

Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 27 February 2020

Our Ref: 23/57262-1-2

Your Ref: 2101

Page: 3 of 5

**Client: Kobefab International B.V.**

## **FIRE TESTS ACCORDING to IMO FTP Code 2010:Part 7**

### **Test for Vertically Supported Textiles and Films**

#### **Cleaning Procedure**

The sample received no pre-treatment as the fabric was stated to be inherently flame retardant.

#### **Conditioning**

The sample was conditioned for 72 hours in the standard atmosphere for conditioning textiles of  $20 \pm 5^\circ\text{C}$  and  $65 \pm 5\% \text{ R.H.}$

#### **Procedure**

The sample was tested in accordance with IMO FTP Code 2010:Part 7. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

A 40mm high propane gas flame was applied to the face of 5 warp and 5 weft specimens for 15 seconds.


The after-flame time, length of char, existence of surface flashing and ignition of cotton waste from drops were recorded.

#### **Requirements**

The Performance Criteria for Curtains and Drapes states that: Products which show any of the following characteristics obtained by the fire test in appendix 1, shall be considered unsuitable for use as curtains, drapes or free-hanging fabric product for use in rooms containing furniture and furnishings of restricted fire risk as defined in the relevant regulations of chapter II-2 of the Convention:-.

1. An after-flame time greater than 5 sec for any of the 10 or more specimens tested with surface application of the pilot flame.
2. Burn through to any edge of any of the 10 or more specimens tested with surface application of the pilot flame.
3. Ignition of cotton wool below specimen in any of the 10 or more specimens tested.
4. An average char length in excess of 150mm observed in any of the 10 or more specimens tested by either surface or edge ignition; and
5. The occurrence of a surface flash propagating more than 100mm from the point of ignition with or without charring of the base fabric.

If it is found that either or both of the batches of five specimens cut in both warp and weft directions fail to meet one or more of the criteria specified in subparagraphs .1 to .3 and .5 above because of poor performance of only one of the five specimens tested, one complete retest of a similar batch is permitted. Failure of the second batch to meet any of the criteria shall provide the basis for rejection of the fabric for use.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Limited

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)

Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 27 February 2020

Our Ref: 23/57262-1-2

Your Ref: 2101

Page: 4 of 5

Client: Kobefab International B.V.

#### As Received

|      | After flame time (s) |      | Char length (mm) |      | Flaming to edge (yes or No) |      | Ignition of Cotton Wool from Flaming Drops (Yes or No) |      | Surface Flashing (Yes or No), if yes, Propagation Length (mm) |      |
|------|----------------------|------|------------------|------|-----------------------------|------|--------------------------------------------------------|------|---------------------------------------------------------------|------|
|      | Warp                 | Weft | Warp             | Warp | Weft                        | Weft | Warp                                                   | Weft | Warp                                                          | Weft |
|      | 0                    | 0    | 66               | 71   | No                          | No   | No                                                     | No   | No                                                            | No   |
|      | 0                    | 0    | 69               | 73   | No                          | No   | No                                                     | No   | No                                                            | No   |
|      | 0                    | 0    | 67               | 77   | No                          | No   | No                                                     | No   | No                                                            | No   |
|      | 0                    | 0    | 65               | 69   | No                          | No   | No                                                     | No   | No                                                            | No   |
|      | 0                    | 0    | 69               | 70   | No                          | No   | No                                                     | No   | No                                                            | No   |
| Mean | 0                    | 0    | 67               | 72   |                             |      |                                                        |      |                                                               |      |

#### Comment

The results indicate the sample meets the requirements according to IMO 2010 FTP Code, Part 7.

This report relates only to the samples submitted and as described in the report.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Reported by:.....

B Bland

Laboratory Technician

Countersigned By:.....

P Doherty

Manager



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.  
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Limited

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2020 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

**Client: Kobefab International B.V.**

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.  
Telephone: +44 (0) 113 259 1999  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)  
Website: [www.bttg.co.uk](http://www.bttg.co.uk)

Date: 27 February 2020

Our Ref: 23/57262-1-2  
Your Ref: 2101

Page: 5 of 5

## Uncertainty Budget - Annex

The overall uncertainty budget IMO FTP Code 2010:Part 7 is as follows:-

Measurements:  $\pm 1\text{mm}$   
Duration of Flaming:  $\pm 0.5$  seconds

