



AB-0716-T

TURT230075912_
REVISED01

07-23

REPORT NUMBER : TURT230075912_REVISED01

APPLICANT NAME **KOBEFAB INTERNATIONAL BV**

ADDRESS KOBEFAB INTERNATIONAL BV De vest 62 Valkenswaard, 5555 XP The Netherlands

Attention : BINI BAJRACHARYA

SAMPLE DESCRIPTION : One sample of cream/mustard/gray woven fabric

DATE IN : 20 July, 2023 (10:38)

DATE OUT : 28 July, 2023 / 31 July, 2023

MODEL STYLE NO: PANDAN FR

ORDER NO: 1878-10486752

END USE: Not Given

COLOUR: 773J1-1

NOTE: Test method and requirement was given by the applicant
In this revised 01 report, Applicant name, address and attention were changed by the request of the applicant.
This report replaces the report no TURT230075912 dated on 28 July, 2023 and must be used instead of it.
Report no TURT230075912 dated on 28 July, 2023 is invalid.

TEST	SAMPLE 1
FLAMMABILITY TEST (CIGARETTE)	P
FLAMMABILITY TEST (MATCH)	P

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE/ LS : LACK OF SAMPLE

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party, nor could it be used for PR activities. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received. Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule.



Merve Tuncer
Customer Care Executive



Nida ARSLANBAY
Textile Laboratory Manager

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No: 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY
Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55
e-mail : intertekcg.turkiye@intertek.com
www.intertek-turkey.com



230075912_REVISED01

Test Method	Result	Requirements
-------------	--------	--------------

Flammability Test- Ignition Source: Match Flame BS EN 1021-2:2014

Test Specification

Side Tested:	Face
Flame Application Time:	15±1 seconds

Filling Specification

Filling Type:	Polyurethane foam
Size:	450 x 300 x 75 mm (back) & 450x150x 75 mm (seat)
Density/Hardness:	20-22 kg/m ³ , Type B Hardness grade130

Pre-treatment / Durability procedure

The sample was water soaked as BS EN 1021-2014 Annex D Line dried.

Conditioning

Prior to testing:	At least 72 hours in ambient indoor conditions, then at least 24 hours in an atmosphere having a temperature of 23±2°C and a relative humidity of 50±5%
At time of testing:	Temperature of 10°C to 30°C and a relative humidity of 15% to 80% Air flow rate of less than 0,2 m/s

Test Method	Pre Treatment	Requirements	Result
BS EN 1021-2: 2014 (Match Flame Equivalent)	*	As BS EN 1021-2: 2014 (Match Flame Equivalent)	PASS

Test Method	Result	Requirements
-------------	--------	--------------

Test Result

"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a mean of assessing the full potential fire hazard of materials in use."

Test number / position	1	2	3
Criterion of ignition			
Smouldering Criteria			
Unsafe escalating combustion (3.1a)	NO	NO	NO
Test assembly consumed (3.1b)	NO	NO	NO
Smoulders to extremities (3.1c)	NO	NO	NO
Smoulders through thickness (3.1c)	NO	NO	NO
Smoulders more than 1 hour (3.1d)	NO	NO	NO
In final examination, presence of active smouldering (3.1e)	NO	NO	NO
Flaming criteria			
Unsafe escalating combustion (3.2a)	NO	NO	NO
Test assembly consumed (3.2b)	NO	NO	NO
Flames to extremities (3.2c)	NO	NO	NO
Flames through thickness (3.2c)	NO	NO	NO
Flames longer than 120 s (3.2d)	NO	NO	NO
Comments			
Flaming ceased	-	-	-
Glowing ceased	-	-	-
Smoke ceased	-	-	-
Result (Non Ignition / Smouldering Ignition / Flaming Ignition)	NI	NI	NI

* The cigarette failed to burn its complete length

Y: Yes N: No NA: Not Applicable P: Pass F: Fail

Test Method	Result	Requirements
-------------	--------	--------------

Flammability Test- Ignition Source: Smouldering Cigarette BS EN 1021-1:2014

Test Specification

Side Tested:	Face
--------------	------

Filling Specification

Filling Type:	Polyurethane foam
Size:	450 x 300 x 75 mm (back) & 450x150x 75 mm (seat)
Density/Hardness:	20-22 kg/m ³ , Type B Hardness grade130

Pre-treatment / Durability procedure

The sample was water soaked as BS EN 1021: 2014 Annex D Line dried.

Conditioning

Prior to testing:	At least 72 hours in ambient indoor conditions, then at least 24 hours in an atmosphere having a temperature of 23±2°C and a relative humidity of 50±5%
At time of testing:	Temperature of 10°C to 30°C and a relative humidity of 15% to 80% Air flow rate of less than 0,2 m/s

Test Method	Pre Treatment	Requirements	Result
BS EN 1021-1: 2014 (Smouldering Cigarette)	*	As BS EN 1021-1: 2014 (Smouldering Cigarette)	PASS

Test Method	Result	Requirements
-------------	--------	--------------

Test Result

"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a mean of assessing the full potential fire hazard of materials in use."

Test number / position	Specimen 1	Specimen 2
Criterion of ignition		
Smouldering Criteria		
Unsafe escalating combustion (3.1a)	NO	NO
Test assembly consumed (3.1b)	NO	NO
Smoulders to extremities (3.1c)	NO	NO
Smoulders through thickness (3.1c)	NO	NO
Smoulders more than 1 hour (3.1d)	NO	NO
In final examination, presence of active smouldering (3.1e)	NO	NO
Flaming criteria		
Occurrence of flames (3.2)	NO	NO
Comments		
Flaming ceased	-	-
Glowing ceased	-	-
Smoke ceased	-	-
Result (Non Ignition / Smouldering Ignition / Flaming Ignition)	NI	NI

* The cigarette failed to burn its complete length

Sonuç ifadeleri:

Y: Yes N: No NA: Not Applicable P: Pass F: Fail

END OF TEST REPORT