



Kobe Fabrics B.V.
La Défense 11
5026 SC TILBURG
Netherlands

Your notice of
06-08-2025

Your reference

Date
15-09-2025

Analysis Report 25.04312.10

Required tests :
BS 5852 (2006)
BS 5852 (2006)

Water soaking procedure
Clause 11 (upholstery composite) - Assessment of the
ignitability of upholstered seating - crib ignition source no. 5

Sample id	Information given by the client	Date of receipt
T2515616	MINT FR	06-08-2025

Mike De Vrieze
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Samples

T2515616
MINT FR





Reference: T2515616 - MINT FR

Water soaking procedure

Date of ending the test 21-08-2025
Standard used BS 5852 (2006)

Deviation from the standard -

The water soaking procedure* is compatible with following standard(s):


BS 5852 (2006)

EN 1021-1 Ann.D (2014)

EN 1021-2 Ann.D (2014)

* Has been carried out based on information given by the client

Sample generated: T2515616_01d



Reference: T2515616_01d - MINT FR

Clause 11 (upholstery composite) - Assessment of the ignitability of upholstered seating - crib ignition source no. 5

Date of ending the test 15-09-2025
Standard used BS 5852 (2006)
Deviation from the standard -
Conditioning 23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Filling S3535 (Eupen Foam Products) * - fire retardant foam - $\pm 35 \text{ kg/m}^3$

* The filling complies with schedule 1 part 1 of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoke, heat or glowing more than 1 hour	no	no
Smoulders more than 100 mm from source	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flames to extremities	no	no
Flames through thickness	no	no
Flame time specimen >10 min	no	no
Flame time specimen	9 min 49 s	6 min 51 s
Flaming debris	no	no
	non-ignition - NI/5	non-ignition - NI/5

Conclusion Non-ignition - NI/5