



Kobe Fabrics B.V.
La Défense 11
5026 SC TILBURG
Netherlands

Your notice of
06-08-2025

Your reference

Date
15-09-2025

Analysis Report 25.04312.06

Required tests :

BS 5852 (2006)
EN 1021-1 (2014)

EN 1021-2 (2014)

Water soaking procedure

Furniture - Assessment of the ignitability of upholstered furniture - Ignition source : smouldering cigarette

Furniture - Assessment of the ignitability of upholstered furniture - Ignition source : match flame equivalent

Sample id	Information given by the client	Date of receipt
T2515616	MINT FR	06-08-2025

Mike De Vrieze
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Samples

T2515616
MINT FR





Reference: T2515616 - MINT FR

Water soaking procedure

Date of ending the test 21-08-2025
Standard used BS 5852 (2006)

Deviation from the standard -

The water soaking procedure* is compatible with following standard(s):

BS 5852 (2006)

EN 1021-1 Ann.D (2014)

EN 1021-2 Ann.D (2014)

* Has been carried out based on information given by the client

Sample generated: T2515616_01d

Reference: T2515616_01d - MINT FR

Furniture - Assessment of the ignitability of upholstered furniture - Ignition source : smouldering cigarette

Date of ending the test 15-09-2025
Standard used EN 1021-1 (2014)
Deviation from the standard -
Conditioning 23°C, relative humidity 50%
Filling T 23140 (Euro-mousse) - non-fire retardant foam - ± 22 kg/m³

	1	2#	3#
Smouldering criteria			
Unsafe escalating combustion	no	no	no
Test assembly consumed	no	no	no
Smoulders to extremities	no	no	no
Smoulders through thickness	no	no	no
Smoulders more than 1 hour	no	no	no
Final examination / active smouldering	no	no	no
Flaming criteria			
Occurrence of flames	no	no	no
	non-ignition	non-ignition	non-ignition

cigarette fails to smoulder its complete length

Conclusion Non-ignition

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Reference: T2515616_01d - MINT FR

Furniture - Assessment of the ignitability of upholstered furniture – Ignition source : match flame equivalent

Date of ending the test 15-09-2025
Standard used EN 1021-2 (2014)
Deviation from the standard -
Conditioning 23°C, relative humidity 50%
Filling T 23140 (Euro-mousse) - non-fire retardant foam - ± 22 kg/m³
Flame application time (s) 15

	1	2	3
Smouldering criteria			
Unsafe escalating combustion	no	no	no
Test assembly consumed	no	no	no
Smoulders to extremities	no	no	no
Smoulders through thickness	no	no	no
Smoke/heat/glowing more than 60 min	no	no	no
Final examination / active smouldering	no	no	no
Flaming criteria			
Unsafe escalating combustion	no	no	no
Test assembly consumed	no	no	no
Flames to extremities	no	no	no
Flames through thickness	no	no	no
Flaming > 120 s	no	no	no
Afterflame time (s)	0	0	0
	non-ignition	non-ignition	non-ignition

Conclusion Non-ignition

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.